

OVERVIEW

IM-Prime is a polymer emulsion-based primer designed to improve the adhesion of self-adhered membranes. IM-Prime is applied to cinder block, concrete, OSB, plywood, DensGlass Gold®, Securock, DensDeck® Prime and prepared metal surfaces.

Improved Adhesion - IM-Prime increases the adhesion of all self-adhering membranes and, in some cases, even increases the adhesion by as much as four times the original adhesion without primer.

Reduces Total Job Time - IM-Prime is formulated to dry tack-free within 2 hours at 77°F (25°C).

Environmentally Friendly - IM-Prime eliminates the flammability and toxicity hazards associated with solvent-based primers. IM-Prime has no irritating or unpleasant odors.

APPLICATION

All surfaces must be in sound condition and free of dirt, debris, and dust. Do not apply to wet surfaces, as this will dilute the primer, reducing its effectiveness. Apply IM-Prime at a rate of 0.5 gal/square (0.21 l/m²) to properly prepared substrates using a medium nap roller or spray equipment (a 0.0155-0.021 inch spray tip orifice and a minimum spray pressure of 500 psi are recommended). Avoid “puddling” the primer. One coat is recommended.

The IM-Prime can withstand foot traffic in about 1-2 hours. Once the primer is applied and allowed to dry, install the Imperflex USA Base sheet, Imperflex MSA, Defend, or MAT-40 system directly to the primed surface. IM-Prime can also be used to promote interply adhesion.

Immediately rinse equipment and tools with water after use. If the material has cured, clean with mineral spirits, using flammable liquid precautions. If skin contact is made, rinse using waterless hand cleaner.

PRECAUTIONS

- Do not allow the product to freeze, do not store in temperatures above 120°F (48°C)
- Do not place in contact with potable water
- Do not thin
- Exterior use only
- Do not use if heavy rain or dew is expected or if temperatures are expected to drop below 50°F (10°C) within 6 hours of application
- Do not install if the outside air temperature is above 95°F (35°C)
- Primer must be covered within 48 hours of application, or an additional coat of primer must be applied

Technical Data	IM-Prime
Density (ASTM D 1475)	8.75 lbs./gal.
Non-Volatile (ASTM D 3960) by Weight by Volume	42-46% 40-44%
Viscosity @77°F (25°C) Brookfield RVT, #4 Spindle; 10 rpm (ASTM D 2196)	2000-2400 cPs
Drying Time @ 70°F (21.1°C); 50% RH To Touch	2 hours
Color	Blue
Shelf Life	1 year
Coverage <i>dependant on the substrate</i>	1/3 to 1/2 gal. per 100 sq. ft. (0.13 - 0.20 l/m ²)
Packaging	5 gal. pail (18.9 l) 55 gal. drum (208.2 l)

Eco Facts	IM-Prime
VOC	< 50 g/L