

Asphalt Primer 41™

PRODUCT INFORMATION



OVERVIEW

Asphalt Primer 41™ is a non fibered, quick drying roof primer. It is made from specially formulated asphalts and penetrating oils. It can also be used to re-saturate existing roof felts and coating to create an elastic bonding surface for Imper-Sol coatings. Asphalt Primer 41 meets and exceeds ASTM D41.

APPLICATION

The surface must be clean and dry prior to an application of Asphalt Primer 41. Any prior roof coatings or improperly bonded materials must be removed prior to application.

should range between 50° - 100°F. For optimum application, the product should be at a minimum of 60°F. Asphalt Primer 41 can be applied by brush, or roller. See BITEC application bulletins for additional information. Asphalt Primer 41 vehicle is a blend of solvents considered combustible by the standards of the D.O.T. and O.S.H.A.

PRECAUTIONS

- Do not use in temperatures above 120°F (48°C)
- Do not place in contact with potable water
- Do not thin
- Exterior use only
- Do not use if heavy rain or dew is expected or if temperatures are expected to drop below 50°F (10° C) within 6 hours of application
- Do not install if the outside air temperature is above 95°F (35°C)
- Primer must be covered within 48 hours of application, or an additional coat of primer must be applied

Technical Data	Asphalt Primer 41
Viscosity by Zahn Cup #2	18 to 20 sec
Covergae Rate	0.5-0.75 gal/100 ft ²
Flashpoint	100°F
VOC	450 g/l
Shelf Life	1 year
Non-Volatile	35%
Wet Mil Thickness	8 - 16 mils
Coverage Rate	.5 - .75 gal/100ft ²



BiTec

P.O. Box 497

No. 2 Industrial Park Drive, Morrilton, Arkansas 72110

Phone 1-800-535-8597

Fax (501) 354-3019

www.bi-tec.com

121521