

Impersol™ EB Rubber Skylight Coating

PRODUCT INFORMATION



OVERVIEW

Impersol EB Rubber Skylight Coating is a clear rubber coating that provides extremely effective protection for fiberglass skylight panels. It is a one-component product that has excellent adhesion to properly prepared surfaces. The coating is thermally stable and resists cracking and peeling due to weather extremes and ultraviolet exposure.

Recommended use: For Skylights Only

APPLICATION INSTRUCTIONS

The surface must be free of any dirt, moisture, oils, algae or other contaminants that may interfere with good adhesion. Carefully remove any loose material from surface with a wire brush or scraper. Grease and oil should also be removed with environmentally safe solvents or an appropriate detergent cleaner such as Impersol Cleaner De-greaser. In most cases a high pressure water blast will be sufficient to prepare the surface.

To obtain the best results, ambient temperatures of the air and the substrate should range between 50° - 100°F. For optimum application, the product should be at a minimum of 60°F.

Impersol EB Rubber Skylight Coating can be applied by brush, or roller. See BITEC application bulletins for additional information.

Impersol EB Rubber Skylight Coating vehicle is a blend of solvents considered combustible by the standards of the D.O.T. and O.S.H.A.

APPLICATION SHOULD BE SUSPENDED IMMEDIATELY AND OUR TECHNICAL SERVICE PERSONNEL CONTACTED IF THE RESULTS BEING OBTAINED ARE LESS THAN DESIRABLE.

HANDLING & STORAGE

Notice: It should be used and stored away from flames, in a well-ventilated atmosphere. Avoid prolonged breathing of vapors and prevent contact with eyes. Read all label information, SDS, and precautions before using. The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.

Technical Data	Skylight Coating
Coverage Rate	80 -100 ft ² /gal
Viscosity (78°F)	1,500 cP
Drying Time	1 - 3 hours
Elongation (ASTM D412)	400%
Tensile Strength(ASTM D412)	1,520 psi
Permeance (10mils) (ASTM E96)	0.166 perms
Color	Clear
Solids	37.1% approximately
Specific Gravity	0.864
Weight	7.2 lb/gal
Flash Point	101°F (38.33° C)
Wet / Dry Mil Thickness	10 - 12 mils / 4 - 5 mils



BITEC

P.O. Box 497

No. 2 Industrial Park Drive, Morrilton, Arkansas

72110 Phone 1-800-535-8597

Fax (501) 354-3019

www.bi-tec.com